

## Cordenka® Growth 400 AC1

Product Description	Compostable rayon based cellulose fiber twine for green house applications
Marking Colour	None
Material Number	150869

## Properties

Property	Unit	Typical Value	Min	Max
Linear Density	dtex	9.250	8.900	9.600
Breaking Force	N	400	370	÷
Elongation at Break	%	12,5	10,0	15,0
Yield	m / kg	1.081	1.042	1.124

All tests performed at cord material conditioned in standard climate (65% rel. humidity, 20 °C) with a cord moisture content of approx. 13%.

Material is compostable, biodegradeable and GMO free.  
Material is developed for indoor greenhouse applications.  
Material should be stored in dry conditions before use.

Development type / Status      04/2024      Technical data subject to change

Manufacturer: Cordenka GmbH & Co. KG  
Industriecenter Obernburg  
63784 Obernburg, Germany  
[www.cordenka.com](http://www.cordenka.com)

**CORDENKA®**

Premium Rayon Reinforcement

The data given in this document constitutes average values. The data and information given are based on our knowledge and experience to date and are not intended for use in component design, nor do they in any way constitute an implied warranty of material properties. Evaluation of the material's suitability for any specific intended application is the sole responsibility of the processor. This document supersedes all previous issues.